NO. 5035 RECEIVED CENTRAL FAX CENTER

SEP 0 2 2005

ROHM AND HAAS COMPANY **FACSIMILE TRANSMITTAL SHEET**

PATENT MAIL STOP AF

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Docket No. A01446

In re application of Thomas Richard Tepe

Serial No.: 10/665,329

Group Art Unit: 1714

Filed: September 18, 2003

Examiner: Vickey M. Ronesi

Thickener for High-Surfactant Aqueous Systems

Mail Stop AF

Commissioner for Patents P.O. Box 1450 Alexandria, VA 22313-1450 Facsimile No. 571-273-8300

CERTIFICATION OF FACSIMILE TRANSMISSION

I hereby certify that the following papers are being facsimile transmitted to the Patent and Trademark Office on the date shown below:

> Amendment under 37 C.F.R. § 1.116 (6 pages) Declaration under 37 C.F.R. § 1.132 (6 pages)

Sender's Facsimile No.: 847-649-3760

Sender's Phone No.:847-649-3891

Number of pages of this facsimile transmission including fax cover sheet 13

The information contained in this facsimile transmission is intended only for the personal and confidential use of the designated recipient named above. This transmittal may be a confidential attorney-client communication or may otherwise be privileged or confidential. If you have received this transmittal in error, any review, dissemination, distribution, or copying of this transmittal or the information which it contains is strictly prohibited. If you have received this transmittal in error, please notify us immediately by telephone and return the original transmittal to us by mail. Thank you.

BEST AVAILABLE COPY

SEP. 2. 2005 3:48PM

ROHM & HAAS CO.

NO. 5035 P. 11

ROHM AND HAAS COMPANY

Page:

100

Date:

07/30/2001

Reference: Project #:

DR3858 1343.15 Sample ID: 38100

Notabook: 72982

Composition:

Objective: Compositonal optimization of DR3858 at 30 % solids by Acusol 820 process

EA Lipol MAA AA DAP R-DDM	70	300.0 71.4 35.7 100.0 1.00 0.50	60.0 10.0 10.0 20.0 0.20 0.10	300.0 50.0 50.0 100.0 1.00 0.50	17.80 4.24 2.12 5.93 0.08 0.03
---------------------------	----	--	--	--	---

Subject matter of pages disclosed to me and understood.

Witness

Work continued

on page_

Diane L. Routzahn

BEST AVAILABLE COPY

SEP. 2. 2005 3:48PM

ROHM & HAAS CO.

NO. 5035

P. 12

ROHM AND HAAS COMPANY

Page :

96

Date:

07/26/2001

Reference: Project#:

DR3858

1343.15

Sample ID: 3896 Notebook: 72982

Composition:

Lifo I MANUSANDE/GO EA/10 MAA/20 AA//0.1 DAP

Objective: Compositonal optimization of DR3858 at 30 % solids by Acusol 820 process

EA EA MAA AA DAP	70	300.0 71.4 35.7 100.0 0.50	60.0 10.0 10.0 20.0 0.1	300.0 50.0 50.0 100.0 0.5	17.81 4.24 2.12 5.94 0.03
----------------------	----	--	-------------------------------------	---------------------------------------	---------------------------------------

Sobject matter of pages disclosed to me and understood.

Witness

Work continued,

DEDI AVAILABLE COPY

SEP. 2.2005 3:48PM

ROHM & HAAS CO.

NO. 5035

Page:

Notebook:

Sample ID: 3824

24

72982

ROHM AND HAAS COMPANY

Work continued

from page Dale:

05/10/2001

Reference:

AGB4352

Project#:

1343.15

Composition:

L; p0 | NF 184 182 | EA/40 MAA/0.2 DAP

Objective: To achieve efficacy, clarify, short rheology, and compatibility in high surfactant concentration

formulations

EA MAA DAP n-DDM	Lipol	70	297.5 182.1 246.9 1.42 0.00	42.0 18.0 40.0 0.20 0.00	297.5 127.5 283.3 1.42 0.00	12.91 7.90 10.71 0.06 0.00
------------------	-------	----	---	--------------------------------------	---	--

Daily Hazard Analysis done

Subject matter of pages _ disclosed to me and understood.

Work continued on page